

Material 50 CR 879

black

cross linking: Metallic oxide

No resampling

revision index	revision date	page	1 / 3
4	10/11/2012		

Physical properties	nominal range	typical values	
Density DIN EN ISO 1183-1	1.35 ±0.02	1.35	g/cm ³
Hardness DIN ISO 7619-1	50 ±5	55	Shore
Rebound resilience DIN 53512	> 30	45	%
Modulus 100 %, DIN 53504, S2	> 2	2.7	MPa
Tensile strength DIN 53504, S2	> 12	15.7	MPa
Elongation at break DIN 53504, S2	> 360	475	%
Compression set DIN ISO 815, 22 h, 100 °C	< 30	25	%

Temperature range -40°C to 100°C

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer
Telefon: +49 6201 80 2182
Fax: +49 6201 88 2182
Email: Daniel.Danzer@fst.com

Material 50 CR 879

black

cross linking: Metallic oxide

No resampling

revision index

4

revision date

10/11/2012

page 2 / 3

Tested after ASTM D 2000: M 2 BC 510 A14 B14 C12 EO14 EO34 F17 G21

		nominal range	typical values
Hardness	Shore	50 ±5	53
Tensile strength	MPa	min. 10	13.1
Elongation at break	%	min. 350	510
A14 Change after aging in Air 70h/100°C			
Hardness	Shore	15	5
Tensile strength	%	-15	2
Elongation at break	%	-40	-5
B14 Compression set 22h/100°C	%	35	32
C12 Ozone Resistance 38°C	%	100	1
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore	±10	8
Tensile strength	%	-30	10
Elongation at break	%	-30	-20
Volume	%	-10 to 15	-9
EO34 Change after aging in IRM 903 70h/100°C			
Tensile strength	%	-70	-25
Elongation at break	%	-55	-35
Volume	%	120	50
F17 Low-temperature resistance after 3 min at -40 °C 3min./-40°C			pass
G21 Tear Resistance < 7 MPa 23°C	MPa	22	36

The material has an excellent ozone and weather resistance. The diesel fuel- and mineral oil resistance is adequate.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer
Telefon: +49 6201 80 2182
Fax: +49 6201 88 2182
Email: Daniel.Danzer@fst.com

Material 50 CR 879

black

cross linking: Metallic oxide

No resampling

revision index

4

revision date

10/11/2012

page 3 / 3

This material contains a SVHC-substance <0,1%.(Imidazolidin-2-thion CAS-No. 96-45-7) in the vulcanized parts.

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Daniel Danzer

Telefon: +49 6201 80 2182

Fax: +49 6201 88 2182

Email: Daniel.Danzer@fst.com