

Technical data sheet in accordance with ASTM

Material

NBR NB707101

black

cross linking: sulfur

| | | | |
|-----------------------|----------------------|-------------|--------------|
| revision index | revision date | page | 1 / 3 |
| 4 | 10/24/2019 | | |

| Physical properties | nominal range | typical values | |
|---|----------------|----------------|-------------------|
| Density ASTM D 1817 | 1.23 ±0.02 | 1.23 | g/cm ³ |
| Hardness ASTM D2240, Shore A | 70 ±5 | 67 | Shore |
| Tensile strength ASTM D412 | --- | 17.5 | MPa |
| Elongation at Break ASTM D412 | --- | 325 | % |
| Low temperature test ASTM D1329, TR10 | --- | -27.1 | °C |
| Low-temperature resistance ASTM D 2137, 3 min, Method C, Nonbrittle; pass | --- | -35 | |
| Compression set ASTM D395, B, 22 h, 100 °C, 25 % | --- | 8 | % |
| Temperature range | -30°C to 100°C | | |

Declarations of conformity

| | Country | Part | Remark | Expires | unlimited |
|--------------|---------|------|--|---------|-------------------------------------|
| ADI Free | | | see certificate | | <input checked="" type="checkbox"/> |
| RoHS conform | | | including EU 2011/65 and EU2015/863 (ROHS III) | | <input checked="" type="checkbox"/> |

Change after aging in Air: 70h/100°C

| | | Typ. values | | |
|---------------------------------|-------|-------------|-------------|------------|
| | | Base value | After aging | difference |
| Hardness (ASTM D2240, Shore A) | Shore | 67 | 71 | 4 |
| Tensile strength (ASTM D412) | MPa | 17.5 | 17.1 | -2 % |
| Elongation at Break (ASTM D412) | % | 325 | 276 | -15 % |
| volume change (ASTM D471) | % | | -0.4 | |

Freudenberg

 Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner

 Telefon: +49 40 66989 279
 Fax: +49 40 66989 9279
 Email: naja.gueldner@fst.com


Technical data sheet in accordance with ASTM

Material

NBR NB707101

black

cross linking: sulfur

revision index

4

revision date

10/24/2019

page 2 / 3

Change after aging in ASTM-Oil No. 1: 70h/100°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at Break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

| Typ. values | | | |
|-------------|-------------|------------|--|
| Base value | After aging | difference | |
| 67 | 76 | 9 | |
| 17.5 | 17.9 | 2 % | |
| 325 | 279 | -14 % | |
| | -9.5 | | |

Change after aging in ASTM-Oil No. 3: 70h/100°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at Break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

| Typ. values | | | |
|-------------|-------------|------------|--|
| Base value | After aging | difference | |
| 67 | 70 | 3 | |
| 17.5 | 17.7 | 1 % | |
| 325 | 286 | -12 % | |
| | 1.6 | | |

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: +49 40 66989 279
Fax: +49 40 66989 9279
Email: nadja.gueldner@fst.com



Technical data sheet in accordance with ASTM

Material

NBR NB707101

black

cross linking: sulfur

revision index

4

revision date

10/24/2019

page 3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: +49 40 66989 279
Fax: +49 40 66989 9279
Email: nadja.gueldner@fst.com

