

Technical data sheet in accordance with ASTM

## Material

### 80 FKM V800M

black

cross linking: bisphenolically

**revision index**

1

**revision date**

7/29/2021

**page**

1 / 2

#### Physical properties

	<b>nominal range</b>	<b>typical values</b>	
<b>Density</b> ASTM D297, 23 °C	---	---	g/cm <sup>3</sup>
<b>Hardness</b> ASTM D2240, Shore A, 23 °C	80 ±5	80	Shore
<b>Tensile strength</b> ASTM D412, C, 23 °C	> 14	15	MPa
<b>Elongation at Break</b> ASTM D412, C, 23 °C	> 150	190	%

#### Declarations of conformity

No data found!

#### Freudenberg

Freudenberg FST GmbH  
Global Material Technology  
Daniel Danzer

Telefon: +49 6201 80 2182

Fax: +49 6201 88 2182

Email: Daniel.Danzer@fst.com

Technical data sheet in accordance with ASTM

## Material

### 80 FKM V800M

black

cross linking: bisphenolically

revision index

revision date

1

7/29/2021

page 2 / 2

Tested after ASTM D 2000: M 2 HK 814 A1-10 B38 EF31 EO78

		nominal range	typical values
Hardness	Shore	80 ±5	0
Tensile strength	MPa	min. 14	0
Elongation at break	%	min. 150	0
<b>A1-10 Change after aging in Air 70h/250°C</b>			
Hardness	Shore A	10	0
Tensile strength	%	-25	0
Elongation at break	%	-25	0
<b>B38 Compression set 22h/200°C</b>		% 50	0
<b>EF31 Change after aging in Fuel C 70h/23°C</b>			
Hardness	Shore	±5	0
Tensile strength	%	-25	0
Elongation at break	%	-20	0
Volume	%	0 to 10	0
<b>EO78 Change after aging in Fluid No. 101 70h/200°C</b>			
Hardness	Shore	-15 to 5	0
Tensile strength	%	-40	0
Elongation at break	%	-20	0
Volume	%	0 to 15	0

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

### Freudenberg

Freudenberg FST GmbH  
Global Material Technology  
Daniel Danzer  
Telefon: +49 6201 80 2182  
Fax: +49 6201 88 2182  
Email: Daniel.Danzer@fst.com